

**RECEIVED
CENTRAL FAX CENTER**

NOV 02 2006

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Appl. No. : 10/525,228 Confirmation No. 7189
Applicant : NAKANISHI *et al.*
Filing of § 371 date : February 22, 2005
TC/A.U. : 1755
Examiner : Green, Anthony J
Docket No. : TAN-349
Customer No. : 62,479

APPENDIX A

1. (Currently amended) A method for preparation of ~~high concentrated nanometer-size~~ fine ~~partieles~~ nanoparticles of organic pigment comprising, after dissolving organic pigment into an organic solvent consisting of an amide solvent, pouring ~~the~~ an obtained pigment solution into a second solution, ~~which is~~ said second solution being compatible with said organic solvent and being a poor solvent to the pigment, by vigorously stirring.

2. (Currently amended) The method for preparation of ~~high concentrated nanometer-size~~ fine ~~partieles~~ nanoparticles of organic pigment of claim 1, wherein the organic pigment is azo pigment, phthalocyanine pigment, quinacridone pigment, isoindolinone pigment, cyanine pigment, merocyanine pigment, fullerene pigment, polycyclic aromatic compound or polydiacetylene pigment.

Application no. 10/525,228
Reply to Office Action of 8/17/06

3. (Currently amended) The method for preparation of ~~high concentrated nanometer-size~~ fine ~~partieles~~ nanoparticles of organic pigment of claim 2, wherein the organic pigment is phthalocyanine pigment or quinacridone pigment.

4. (Currently amended) The method for preparation of ~~high concentrated nanometer-size~~ fine ~~partieles~~ nanoparticles of organic pigment of claim 3, wherein the amide solvent is ~~at least the one~~ selected from the group consisting of 1-methyl-2-pyrrolidinone, ~~1,3-dimethyl-2-imidazolidinone~~ 1,3-dimethyl-2-imidazolidinone, 2-pyrrolidinone, ϵ -caprolactam, formamide, N-methylformamide, N,N-dimethylformamide, acetoamide, N-methylacetoamide, N,N-dimethylacetoamide, N-methylpropaneamide and hexamethylphosphotriamide.

5. (Currently amended) The method for preparation of ~~high concentrated nanometer-size~~ fine ~~partieles~~ nanoparticles of organic pigment of claim 1, wherein the amide solvent is ~~at least the one~~ selected from the group consisting of 1-methyl-2-pyrrolidinon, ~~1,3-dimethyl-2-imidazolidinone~~ 1,3-dimethyl-2-imidazolidinone, 2-pyrrolidinone, ϵ -caprolactam, formamide, N-methylformamide, N,N-dimethylformamide, acetoamide, N-methylacetoamide, N,N-dimethylacetoamide, N-methylpropaneamide and hexamethylphosphotriamide.

6. (Currently amended) The method for preparation of ~~high concentrated nanometer-size~~ fine ~~partieles~~ nanoparticles of organic pigment of claim 2, wherein the amide solvent is ~~at least~~

Application no. 10/525,228
Reply to Office Action of 8/17/06

~~the one~~ selected from the group consisting of 1-methyl-2-pyrrolidinone, ~~1,3-dimethyl-2-imidazolidinone~~ 1,3-dimethyl-2-imidazolidinone, 2-pyrrolidinone, ε-caprolactam, formamide, N-methylformamide, N,N-dimethylformamide, acetoamide, N-methylacetoamide, N,N-dimethylacetoamide, N-methylpropanamide and hexamethylphosphotriamide.

7. (Currently amended) The method for preparation of ~~high concentrated nanometer-size~~ fine ~~particles~~ nanoparticles of organic pigment of claim 1, wherein poor solvent is water, alcohol solvents, ketone solvents, ether solvents, aromatic solvents, carbon disulfide, aliphatic solvents, nitrile solvents, sulfoxide solvents, halide solvents, ester solvents, ionic solution or a mixed solution consisting mixture of these two or more thereof solvents.

8. (Currently amended) The method for preparation of ~~high concentrated nanometer-size~~ fine ~~particles~~ nanoparticles of organic pigment of claim 2, wherein poor solvent is water, alcohol solvents, ketone solvents, ether solvents, aromatic solvents, carbon disulfide, aliphatic solvents, nitrile solvents, sulfoxide solvents, halide solvents, ester solvents, ionic solution or a mixed solution consisting mixture of these two or more thereof solvents.

9. (Currently amended) The method for preparation of ~~high concentrated nanometer-size~~ fine ~~particles~~ nanoparticles of organic pigment of claim 3, wherein poor solvent is water, alcohol solvents, ketone solvents, ether solvents, aromatic solvents, carbon disulfide, aliphatic solvents,

Application no. 10/525,228
Reply to Office Action of 8/17/06

nitrile solvents, sulfoxide solvents, halide solvents, ester solvents, ionic solution or a mixed solution consisting mixture of these two or more thereof solvents.

10. (Currently amended) The method for preparation of high concentrated nanometer-size fine ~~particles~~ nanoparticles of organic pigment of claim 4, wherein poor solvent is water, alcohol solvents, ketone solvents, ether solvents, aromatic solvents, carbon disulfide, aliphatic solvents, nitrile solvents, sulfoxide solvents, halide solvents, ester solvents, ionic solution or a mixed solution consisting mixture of these two or more thereof solvents.

11. (Currently amended) The method for preparation of concentrated nanometer-size fine ~~particles~~ nanoparticles of organic pigment of claim 2, using wherein said organic solvent is consisting of at least the one selected from the group consisting of 1-methyl-2-pyrrolidinone, 2-pyrrolidinone or 1,3-dimethyl-2-imidazolidinone, 1,3-dimethyl-2-imidazolidinone or and a mixed amide organic solvent containing 1-methyl-2-pyrrolidinone, 2-pyrrolidinone or 1,3-dimethyl-2-imidazolidinone said solvents in an amount that is more than 50 volume % as a solvent for of the organic solvent, and said using water and/or alcoholic solvent as a poor solvent is water and/or alcoholic solvent.

12. (Currently amended) The method for preparation of concentrated nanometer-size fine ~~particles~~ nanoparticles of claim 3, using wherein said organic solvent is consisting of at least the

Application no. 10/525,228
Reply to Office Action of 8/17/06

~~one~~ selected from the group consisting of 1-methyl-2-pyrrolidinone, 2-pyrrolidinone ~~or 1,3-~~
~~dimethyl-2-imidazolidinone~~ , 1,3-dimethyl-2-imidazolidinone ~~or and~~ a mixed amide organic
solvent containing 1-methyl-2-pyrrolidinone, 2-pyrrolidinone or 1,3-dimethyl-2-imidazolidinone
~~said solvents in an amount that is~~ more than 50 volume % ~~as a solvent for~~ of the organic solvent,
and ~~said using water and/or alcoholic solvent as a poor solvent is~~ water and/or alcoholic solvent.

13. (Currently amended) The method for preparation of concentrated ~~nanometer-size~~ fine
~~partieles~~ nanoparticles of claim 1 comprising, carrying out the preparation of said organic
solution by dissolving an organic pigment by ~~the~~ a condition from heating at around maximum
boiling point under atmospheric pressure to heating under supercritical state, then pouring the
~~prepared high concentrated~~ organic pigment solution of 0.5 mmol/L to 100 mmol/L into a poor
solvent of ~~the~~ a lowest temperature of a liquid state.

14. (Currently amended) The method for preparation of concentrated ~~nanometer-size~~ fine
~~partieles~~ nanoparticles of claim 2 comprising, carrying out the preparation of said organic
solution by dissolving an organic pigment by ~~the~~ a condition from heating at around maximum
boiling point under atmospheric pressure to heating under supercritical state, then pouring the
~~prepared high concentrated~~ organic pigment solution of 0.5 mmol/L to 100 mmol/L into a poor
solvent of ~~the~~ a lowest temperature of a liquid state.

Application no. 10/525,228
Reply to Office Action of 8/17/06

15. (Currently amended) The method for preparation of concentrated ~~nanometer-size~~ fine ~~partieles~~ nanoparticles of claim 3 comprising, carrying out ~~the~~ preparation of said organic solution by dissolving an organic pigment by ~~the~~ a condition from heating at around maximum boiling point under atmospheric pressure to heating under supercritical state, then pouring the ~~prepared high-concentrated organic pigment~~ solution of 0.5 mmol/L to 100 mmol/L into a poor solvent of ~~the~~ a lowest temperature of a liquid state.

16. (Currently amended) The method for preparation of concentrated ~~nanometer-size~~ fine ~~partieles~~ nanoparticles of claim 4 comprising, carrying out ~~the~~ preparation of said organic solution by dissolving an organic pigment by ~~the~~ a condition from heating at around maximum boiling point under atmospheric pressure to heating under supercritical state, then pouring the ~~prepared high-concentrated organic pigment~~ solution of 0.5 mmol/L to 100 mmol/L into a poor solvent of ~~the~~ a lowest temperature of a liquid state.

17. (Currently amended) The method for preparation of concentrated ~~nanometer-size~~ fine ~~partieles~~ nanoparticles of claim 5 comprising, carrying out ~~the~~ preparation of said organic solution by dissolving an organic pigment by ~~the~~ a condition from heating at around maximum boiling point under atmospheric pressure to heating under supercritical state, then pouring the ~~prepared high-concentrated organic pigment~~ solution of 0.5 mmol/L to 100 mmol/L into a poor solvent of ~~the~~ a lowest temperature of a liquid state.